

Clear-Tite® 51/52 HD Shrink Bags

Applications

Clear-Tite® 51/52 HD range of barrier shrink bags are ideally suited for processed meats with spices and hard surfaces, hard rind cheeses and some bone-in meats. These highly shrinkable bags have a superior puncture resistance and provide a glossy surface making it perfect for both retail and industrial applications; as well as enhancing product branding through flexographic printing.

Features

| Seal Type | Seal Format | Width (mm) | Length (mm) | Presentation | Printed |
|----------------|--------------------------|------------|-------------|----------------------|----------------|
| End Seal (52) | Arc, Bar, Profile | 200 - 550 | 250 - 1200 | Loose / Taped / BOAR | Max 10 Colours |
| Side Seal (51) | Straight, Mod Arc, V Arc | 90 - 350 | 200 - 550 | Loose / Taped | Max 10 Colours |

Properties

| Gauge | Oxygen Barrier (cc/m ² /24hrs. @23°C, 0% RH, 1 atm) | Moisture Barrier (g/m ² /24hrs. @38°C, 90% RH, 1 atm) | Shrink % @90°C (MD/TD) | Haze % | Gloss Hu (45°) |
|-------|--|--|------------------------------|--------|-------------------|
| 67μ | 16 | 8 | 45/49 | 9 | 70 |



Storage – Handling

Store in a cool, dry place, away from heat & direct sunlight. Recommended storage temperature : 4°- 24°C (maximum). Use oldest stock first. Store cartons with product label showing. To avoid damage to bags do not use knives, sharp instruments or hooks to open cartons. Store in original packaging and use within 1 year from date of manufacture.

EU Status: All Bemis Swansea products comply with UK Regulations & various EU Regulations including 10/2011, as amended, 1935/2004 & 94/62/EC. Bemis Swansea is registered with LRQA & certified to ISO9001:2008 & BRC/IOP.

IMPORTANT NOTICE TO PURCHASER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. Other sampling or test procedures may produce different values or results. Before using, the user shall determine the suitability of the product or information for his intended use by appropriate testing, sampling and statistical analysis and the user assumes all risk and liability whatsoever in connection therewith. No statement or suggestion herein is to be considered a recommendation or inducement of any use, manufacture or sale that may infringe any patents now or hereafter in existence. Rev 12/01